

**SPECIFICATION**

Issued by : Praphassorn K. Effective date: 15/12/2012

Approved by : Peerapong E.

Document No. SP-MK-140

Ref. 7.2

Edition No. 7

Index no. 8

Page 1 ( 1 )

**PRODUCT SPECIFICATION: aA-COPY**

UNCONTROLLED COPY

Nominal grammage, g/m <sup>2</sup>	80
Basis weight, g/m <sup>2</sup>	77 - 83
Moisture, %	3.0 - 4.0
Thickness, μm	103 - 110
Surface roughness TS ml/min	50 - 125
Surface roughness BS ml/min	75 - 150
Bending stiffness MD, mN	>110
Bending stiffness CD, mN	>50
Opacity, %	>94
Brightness, %	101 - 104
CIE Whiteness	148 - 152

The quality specification is to be used for information only and must not be used as a legal document.

The specification refers to an average of a composite sample withdrawn from a lot with random sampling according to ISO 186 : 2002

**Testing conditions:**

Relative humidity 50%, Temp. 23 °C ISO 187 : 1990

**Testing methods:**

Thickness measurement on single sheets ISO 534 : 2005  
Surface roughness according to Bendtsen ISO 8791 - 2 : 1990  
Bending stiffness according to ISO 2493 : 1992  
D65-Brightness according to ISO 2470 : 1999  
Opacity according to ISO 2471 : 1998  
CIE Whiteness according to ISO 11475 : 2004